## ABSTRACT OF THE DISCLOSURE

A method for fabricating a film bulk acoustic resonator (FBAR) includes depositing a dielectric layer on a substrate, providing a sacrificial layer on part of the dielectric layer; providing a bottom electrode on part of the sacrificial layer on part of the dielectric layer; providing a piezoelectric layer on the bottom electrode; patterning a top electrode on the piezoelectric layer; and removing the sacrificial layer. The substrate may have a cavity receiving the sacrificial layer. As a result, a cantilevered resonator having an air gap between the bottom electrode and the dielectric layer may be simply fabricated.